




SAQ
SIAT

TECHNICAL SPECIFICATION COLD ROLLED FLAT

Document
Revision
Date
Page

SPS105
01 i
18.09.2014
1/2



1. DESCRIPTION.

High quality cold rolled flat from low carbon wire rod according to standard EN 10139.

2. CHEMICAL COMPOSITION ON PRODUCT

Limits	C %	Mn %	Si %	P %	S %
Min	-	-	-	-	-
max	0.10	0.50	0.30	0.040	0.040

NOTE:

Materials for hot zinc galvanising available on request.

Materials with lower carbon percentage available on request.

3. DIMENSIONAL PROPERTIES

Flats		width																															
		7	8	9	10	11	12	13	14	15	16	17	18	19	20	21	22	23	24	25	26	27	28	29	30								
thickness	1,7																																
	1,8																																
	1,9																																
	2																																
	3																																
	4																																
	5																																
	6																																
	7																																
	8																																
	9																																
	10																																
	11																																
	12																																

4. STANDARD PACKAGING

Packaging	Weight Kg.	Nominal dimensions (mm)		
		Int D	Ext D	H
Spoiled coils	1000 ÷ 1500	500/540/600	1.100 max	500

NOTE:

Coils strapped at 4 points with 3/4" metallic strap with metal seals

On request:


Coils on 2 wood sticks size 80x80 mm or 100x100 mm

Coils protected with plastic coating

All data/information of this document are only at informative title and not binding for SIAT S.p.A., who entitles full right to modify/change them without prior notice.



SAQ
SIAT



**TECHNICAL SPECIFICATION
COLD ROLLED FLAT**

Document
Revision
Date
Page

SPS105
01 i
18.09.2014
2/2

5. LABELLING.

Standard SIAT barcode label reporting:

heat nr. – coil nr. - customer name – date of production – size – weight.

6. STANDARD CERTIFICATION.

In accordance to EN 10204 2.2

Certification EN 10204 3.1 on request.